

biosar

Empfohlen von den wichtigsten Herstellern von Heizkesseln und Öfen.
 Recommandé par les principaux fabricants de chaudières et poêles.
 Consigliato dai principali produttori di caldaie e stufe.
 Recommended by the main manufacturers of boilers and stoves.
 Recomendado por los principales fabricantes de calderas y estufas.



77
sacchi sacs
sacos sacks
sacs
15 kg

11 x 7
1600 mm

PALLET
1,155 kg

70
sacchi sacs
sacos sacks
sacs
15 kg


10 x 7
1450 mm

PALLET
1,050 kg

104
sacchi sacs
sacos sacks
sacs
10 kg

13 x 8
1650 mm

PALLET
1,040 kg



Wassergehalt Humidité Umidità Moisture Humedad	5,9%	≤ 10,0%
	*NAPARPELLET	ENPlusA1 - DINPlus
Mechanische Festigkeit Durabilité mécanique Durabilità meccanica Mechanical Durability Durabilidad mecánica	98,9 %	≥ 98,0%
	*NAPARPELLET	ENPlusA1 - DINPlus
Heizwert / Heizwert Hu Pouvoir Calorifique Inférieur (PCI) Potere calorifico inferiore Net Calorific Value Poder calorífico neto	4,9 - 5,3 kwh/kg	≥ 4,6 kwh/kg
	*NAPARPELLET	ENPlusA1 - DINPlus

100% Kiefer. Ohne Rinde und Zusatzstoffe
 Résineux. Sans écorce ni additifs
 Pino. Nessuna corteccia o additivi
 Pine tree. No bark or additives
 Pino. Sin corteza ni aditivos

Feinanteil Fines Polveri Fines Finos	0,2 0%	≤ 0,5%
	*NAPARPELLET	ENPlusA1 - DINPlus
Aschegehalt Taux de cendre (550°C) Ceneri (550°C) Ash (550°C) Cenizas (550°C)	0,4%	≤ 0,70% (ENPlus A1) ≤ 0,60% (DINPlus)
	*NAPARPELLET	ENPlusA1 - DINPlus

*Ergebnisse aus dem Durchschnitt der regelmäßigen Audits und externen Überraschungen, die in den letzten 3 Jahren aufgezeichnet wurden.
 *Résultats et valeurs moyennes des analyses et audits périodiques et inopinés enregistrés au cours des 3 dernières années.
 *Resultati e valori medi delle analisi e degli audit periodici e senza preavviso registrati negli ultimi 3 anni.
 *Results obtained from the average of periodic and surprise audits recorded in the last 3 years.
 *Resultados obtenidos de la media de las auditorías periódicas y sorpresa externas registradas en los últimos 3 años.

